

A high temperature superconducting rotor (15) for a synchronous machine includes a high temperature superconducting field winding (35), a field winding support (30) concentrically arranged about the high temperature superconducting field winding (35), and a thermal reserve (40) concentrically arranged about the field winding support (30). The thermal reserve (30) includes a thermally conductive material. The material is either electrically conductive, for example, aluminum, or electrically non-conductive, for example, ceramics such as beryllium oxide or alumina. The thermal reserve material includes segmentation in a direction normal to the rotor axis, along the rotor axis, neither, or both. The rotor (15) includes a banding (50) concentrically arranged about the thermal reserve (40). The banding (50) includes an electrically conductive material, for example, steel, an electrically non-conductive material, for example, Kevlar, or both. The rotor (15) includes an outer layer (60) concentrically arranged about the thermal reserve (40). The outer layer (60) includes a thermally non-conductive material.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

HIGH TEMPERATURE SUPERCONDUCTING ROTOR
FOR A SYNCHRONOUS MACHINE

5 Background of the Invention

This invention relates to a high temperature superconducting rotor for a synchronous machine.

Typically, a superconducting winding of the rotor in a superconducting machine is cooled with a cryogenic
10 refrigeration system. In the event of a refrigeration system failure, the superconducting winding will heat and eventually quench, leading to total machine failure.

Summary of the Invention

A rotor having a thermal reserve arranged about a
15 high temperature superconducting (HTS) winding is provided. In the event of a refrigeration system failure, the thermal reserve absorbs thermal energy from the HTS winding, thereby reducing the rate of increase of the temperature of the superconducting winding.

20 In accordance with one aspect of the invention, a high temperature superconducting rotor is provided including a high temperature superconducting field winding, a field winding support concentrically arranged about the high temperature superconducting field winding,
25 and a thermal reserve concentrically arranged about the field winding support.

Embodiments of this aspect of the invention may include one or more of the following features.

The thermal reserve includes a thermally
30 conductive material. The material is electrically conductive, for example, aluminum. The material includes segmentation normal to the rotor axis, along the rotor axis, or both. The material, for example, aluminum, is shrunk fit over the field winding support.

- 2 -

Alternatively, the thermal reserve includes a material that is electrically nonconductive, for example, a ceramic, including beryllium oxide or alumina.

The rotor includes a banding concentrically
5. arranged about the thermal reserve. The banding includes an electrically conductive material, for example, steel, an electrically nonconductive material, for example, Kevlar or glass fiber, or both. The banding includes segmentation normal to the rotor axis.

10 The rotor includes an outer layer concentrically arranged about the thermal reserve. The outer layer includes a thermally nonconductive material. The outer layer includes either electrically conductive materials, electrically nonconductive materials, or both.

15 Electrically conductive materials in the outer layer are configured to prevent the flow of eddy currents; for example, a layer of aluminum coated mylar is used. The aluminum coating includes segments. A banding is concentrically arranged about the outer layer.

20 In accordance with another aspect of the invention, a superconducting machine has a rotor. The rotor includes a high temperature superconducting field winding and a field winding support for securing the field winding. The support is electrically isolated from
25 the field winding. An AC flux shield is concentrically arranged about the field winding. A thermal reserve is concentrically arranged about the AC flux shield. The machine further includes a stator concentrically arranged about the rotor.

30 In accordance with an embodiment of this aspect of the invention, a cryogenic refrigeration system is thermally coupled to the rotor.

In accordance with another aspect of the invention, a method is provided for limiting the rate of
35 increase in the temperature of a superconducting winding.

- 3 -

The method includes concentrically arranging a thermal reserve about and in thermal contact with the superconducting winding.

Embodiments of this aspect of the invention may include one or more of the following features.

The invention includes within the thermal reserve a thermally conducting material. Within the thermal reserve, an electrically nonconductive material is disposed between segments of an electrically conductive material. Within the thermal reserve, configuring the electrically nonconductive material to suppress eddy currents. The invention further includes concentrically arranging a thermally nonconductive material about the thermally conducting material.

Brief Description of the Drawings

Fig. 1 is a diagrammatic illustration of the rotor and stator assemblies of a superconducting machine.

Fig. 2 is a cut-away view of the rotor assembly of Fig. 1.

Fig. 3 is a perspective view of the rotor assembly of Fig. 2 with a banding surrounding a thermal reserve.

Fig. 4 is a cross-sectional view of the rotor assembly of Fig. 2 with a thermal reserve segmented along the axis of the rotor.

Fig. 5A is a depiction of an outer layer that is applied to the rotor assembly.

Fig. 5B is a depiction of the aluminum portion of the outer layer shown in Fig. 5A.

Fig. 6 is a perspective view of the rotor assembly of Fig. 2 with the thermal reserve segmented normal to the axis of the rotor.

Description of the Preferred Embodiment

Referring to Fig. 1, a superconducting machine 10, for example, a motor or generator, includes a rotor assembly 15 and a stator assembly 20 concentrically

- 4 -

arranged about rotor assembly 15. At the center 18 of rotor assembly 15 is a drive shaft 25. Rotor assembly 15 is attached to drive shaft 25 to rotate with drive shaft 25. Stator assembly 20 is stationary and includes a frame 45 and a stator winding 48.

Rotor assembly 15 includes a rotor winding support 30 concentrically arranged about drive shaft 25 and enclosing rotor winding 35. Rotor winding 35 is made of a high temperature superconducting material of the type that operates in the temperature range of 20-40 K. Rotor winding 35 is made, for example, using the react-and-wind method, as known in the art, or using a wind-and-react method, as described in Manlief et al., U.S. Patent No. 5,798,678, entitled "Superconducting Wind-and-React-Coils and Methods of Manufacture," hereby incorporated by reference, or as described in Gamble et al., U.S. Patent No. 5,777,420, entitled "Superconducting Synchronous Motor Construction," hereby incorporated by reference.

An AC flux shield 38 is concentrically arranged about winding support 30 preventing AC currents generated during motor transients from reaching rotor winding 35.

Referring also to Fig. 2, rotor winding support 30 is made out of aluminum or other suitable structural material. Rotor winding support 30 acts as an AC flux shield if made from aluminum, copper, steel, or other electrically conductive material (for example, a material having an electrical resistivity of up to about 50 micro-ohms-cm), dispensing with the need to have a separate AC flux shield 38 as shown in Fig. 1.

Concentrically arranged about winding support 30 is a thermal reserve 40 thermally coupled to rotor winding 35 by rotor winding support 30. Concentrically arranged around thermal reserve 40 is a banding 50. Banding 50 secures thermal reserve 40 to rotor winding support 30.

- 5 -

Referring to Fig. 3, banding 50 is formed from a metallic material, such as steel, which is segmented along a cross-sectional plane normal to axis 53 of rotor assembly 15. Segmentation of banding 50 is achieved by placing multiple individual bands (three are shown) around thermal reserve 40. This structure electrically isolates each individual band 52 preventing current flow in a direction along axis 53 of rotor assembly 15. The isolation is provided by a gap 55 between the individual bands. Referring again to Fig. 2, surrounding the banding is an outer layer 60 that shields rotor assembly 15 from heat generated by stator winding 48.

Connected to drive shaft 25 is a refrigeration system, for example, a cryocooler 70 operating with cold helium gas, for cooling rotor winding 35 during normal operation. Cold helium gas for cooling is fed through a port 72 in drive shaft 25. Ducts (not shown) in drive shaft 25 circulate the cold helium gas around rotor winding 35 to draw heat from rotor assembly 15. Cooling is aided by the use of cooling channels in both winding support 30 and thermal reserve 40.

In the event of cryocooler failure, heat buildup in rotor winding 35 causes rotor winding 35 to lose its superconducting characteristics. The rate of heat buildup is reduced, however, by thermal reserve 40. Thermal reserve 40 is thermally conductive, having a thermal conductivity sufficiently high to limit the temperature differential between thermal reserve 40 and winding 35 to some predetermined value. The predetermined value is dependent upon the specific application. In the disclosed embodiment, the thermal reserve has a sufficient thermal conductivity to limit the temperature differential at the boundary between thermal reserve 40 and winding 35 to at most, for example, about 10 K. Preferably, the differential will

- 6 -

be less than 5 K. Even more preferably, the differential will be about 1 K. Thermal reserve 40 absorbs heat generated by rotor winding 35, decreasing the rate at which rotor winding 35 increases in temperature, 5 prolonging the period in which rotor winding 35 remains within the superconducting temperature range.

Referring to Fig. 4 (in which for ease of discussion, rotor winding 35 and rotor winding support 30 are illustrated as a single structure -- rotor winding 10 combination 33), thermal reserve 40 is shown divided into five segments 80 along axis 53 of rotor assembly 15. Each segment 80 is, for example, made of aluminum and is electrically isolated from the other segments by an electrically insulating material 85 made of, for example, 15 metal oxides, epoxies, or Kapton[®], a registered trademark of E. I. du Pont de Nemours and Company. The segmentation suppress eddy currents otherwise resulting from the fields produced by stator winding 48. These eddy currents would produce heat losses in thermal 20 reserve 40 decreasing the efficiency of the machine and reducing the time of operation during cryocooler failure.

The additional operation time provided by thermal reserve 40 in the event of cryocooler failure is calculated by comparing the temperature increase of rotor 25 winding combination 33 without thermal reserve 40 with rotor winding combination 33 surrounded by thermal reserve 40.

The field winding combination 33 has an inner radius R1, for example, 0.5 meters (the radius of drive 30 shaft 25), an outer radius R2, for example, 0.53175

- 7 -

meters, and a length, for example, 0.6096 m. The volume of the field winding combination is:

$$\pi * (0.53175m^2 - 0.5m^2) * 0.6096m = 6.274 * 10^4 cm^3$$

If field winding support 30 is made of aluminum, the specific heat of field winding combination 33 can be
 5 roughly approximated as equal to the specific heat of aluminum, which at 25 K is:

$$\eta = 3.5 * 10^5 \frac{joule}{m^3 * K}$$

The heat capacity of winding combination 33 is determined by multiplying the volume of winding combination 33 by
 10 the specific heat and by the acceptable change in temperature. The acceptable change in temperature is determined by subtracting the normal operating temperature of rotor winding 35 from the maximum
 15 operating temperature, which is the quench temperature of rotor winding 35 decreased for some margin of safety. Typically, this maximum operating temperature will be 5 K above the normal operating temperature. The heat capacity of winding combination 33 under these conditions
 20 is:

$$Q_{capacity} = 6.274 * 10^4 cm^3 * 3.5 * 10^5 \frac{joule}{m^3 * K} * 5K = 1.098 * 10^5 joule$$

- 8 -

The operating time following cryocooler failure is

calculated by dividing the heat capacity of rotor winding combination 33 by the power loss in the field winding.

Once this time is reached, the power loss will have

- 5 heated the winding combination 33 to the maximum acceptable operating temperature. Typically, a superconducting machine will have a power loss in the superconducting winding of 25 watts, resulting in an operating time after cryocooler failure of 1.22 hours.

$$Time = \frac{1.098 \times 10^5 \text{ joules}}{25 \text{ watts}} = 1.22 \text{ hours}$$

- 10 The operating time after cryocooler failure will now be calculated with the addition of thermal reserve 40. Thermal reserve 40 is, for example, constructed from aluminum and has a thickness, t , of 0.0381 m. The volume of thermal reserve 40 is:

$$\pi * (0.5699^2 m - 0.53175^2 m) * .6096 m = 8.038 * 10^4 cm^3$$

- 15 The heat capacity of thermal reserve 40 is the volume multiplied by the specific heat of the material used, in this example, aluminum:

$$Q_{\text{capacity-T.R.}} = 8.038 * 10^4 cm^3 * 3.5 * 10^5 \frac{\text{joule}}{m^3 * K} * 5K = 1.407 * 10^5 \text{ joule}$$

- 9 -

Assuming the same 25 watt loss in field winding 35 as in the prior example, but this time adding together the heat capacities of rotor winding combination 33 and thermal reserve 40 with the preferred thermal conductivity, the operation time available following a cryogenic refrigeration failure is:

$$Time = \frac{1.407 * 10^5 \text{joules} + 1.098 * 10^5 \text{joules}}{25 \text{watts}} = 2.783 \text{hours}$$

Accordingly, the use of thermal reserve 40 with the indicated dimensions keeps the high temperature superconducting machine in operation for more than one and a half additional hours. During this additional time, a repair crew notified of the refrigeration system failure can much more likely repair or replace the refrigeration system, keeping the machine in operation.

Outer layer 60, shown in Fig. 2, will now be described in greater detail. Referring to Fig. 5A, outer layer 60 is composed of a multi-layer insulation, made of an interior layer 64 attached to a thin strong exterior layer material 66. Interior layer 64 is made of, for example, many layers of aluminized mylar. Surrounding interior layer 64 is an exterior layer 66, preferably 1/16 inch thick, of Kevlar or other strong material, such as steel, a composite of G10 materials, or fiber reenforced epoxies.

Referring to Fig. 5B, the aluminum of interior layer 64 is segmented with slots 68. Slots 68 are arranged so eddy currents are suppressed.

Referring again to Fig. 1, stator winding 48 is made of conventional nonsuperconducting wire and is water cooled by the inclusion of cooling tubes (not shown) both

- 10 -

interwound with stator winding 48 and enclosed within frame 45. There is sufficient increase in efficiency, power transfer, and size reduction with the rotor winding alone being made of a superconducting material. Frame 45
5 is made of any suitable strong material, such as steel.

Alternative embodiments are within the scope of the following claims. For example, thermal reserve 40 can be divided into 8, 10, or even more segments. In yet another alternative embodiment, shown in Fig. 6, thermal
10 reserve 40 is segmented normal to axis 53 to prevent the flow of currents in the direction along the axis of the rotor, but segment-free along axis 53. Thick disks of material 100 are aligned along axis 53 and each disk 100 is concentrically arranged about winding combination 33.
15 Each disk 100 is electrically isolated from the others by an insulating material 105. For example, each disk 100 is made of aluminum and may be shrunk fit over the winding combination 33.

In certain circumstances, the ease of construction
20 of the rotor of Fig. 6 outweighs the losses generated by not segmenting the aluminum in a direction along the axis of the rotor. It may also be desirable in certain applications to segment thermal reserve 40 in the directions both normal to and along axis 53 of the rotor
25 in order to suppress both axial and normal currents.

In yet another embodiment, thermal reserve 40 is made of an electrically nonconductive material, for example, beryllium oxide or alumina. The use of an electrically nonconductive material prevents eddy
30 currents from being generated in thermal reserve 40.

In other embodiments, banding 50 is modified by inserting a nonconductive material between the individual conductive bands. By providing a nonconductive material of sufficient strength, such as Kevlar, glass filaments
35 or fibers, or any other high-strength electrically

- 11 -

nonconductive material, the nonconductive material also acts as a banding. Alternatively, banding 50 is made entirely of nonconductive materials.

In yet other embodiments, exterior layer 66 of
5 outer layer 60 is of sufficient strength to also serve as banding 50. In this case, exterior layer 66 is provided with a greater thickness than would otherwise be necessary to secure outer layer 60 alone to rotor
assembly 15. Exterior layer 66 can also be segmented
10 normal to axis 53 of rotor assembly 15.

In other embodiments, rotor winding support 30 is made of an electrically nonconductive material.

What is claimed is:

- 12 -

1. A high temperature superconducting rotor,
comprising:
 - a high temperature superconducting field winding,
 - a field winding support concentrically arranged
5 about the high temperature superconductor field winding,
and
 - a thermal reserve concentrically arranged about
the field winding support.
- 10 2. The rotor of claim 1 wherein the thermal
reserve comprises a material that is thermally
conductive.
3. The rotor of claim 2 wherein the thermal
reserve comprises a material that is electrically
nonconductive.
- 15 4. The rotor of claim 3 wherein the thermal
reserve comprises a ceramic material.
5. The rotor of claim 3 wherein the thermal
reserve comprises Alumina.
6. The rotor of claim 3 wherein the thermal
20 reserve comprises Beryllium Oxide.
7. The rotor of claim 2 wherein the thermal
reserve comprises an electrically conductive material.
8. The rotor of claim 7 wherein the electrically
conductive material includes segmentation in a direction
25 normal to the axis of the rotor.
9. The rotor of claim 7 wherein the electrically
conductive material includes segmentation in a direction
along the axis of the rotor.

- 13 -

10. The rotor of claim 7 wherein the electrically conductive material comprises aluminum shrunk fit over the field winding support.
11. The rotor of claim 1 further comprising a
5 banding concentrically arranged about the thermal reserve.
12. The rotor of claim 11 wherein the banding comprises an electrically conductive material.
13. The rotor of claim 12 wherein the
10 electrically conductive material includes segmentation in a direction normal to the axis of the rotor.
14. The rotor of claim 11 wherein the banding comprises an electrically nonconductive material.
15. The rotor of claim 14 wherein the banding
15 comprises Kevlar.
16. The rotor of claim 14 wherein the banding comprises glass fiber.
17. The rotor of claim 1 further comprising an
outer layer concentrically arranged about the thermal
20 reserve, the outer layer comprising a thermally non-
conductive material
18. The rotor of claim 17 wherein the outer layer comprises an electrically nonconductive material.
19. The rotor of claim 17 wherein the outer layer
25 comprises an electrically conductive material.

- 14 -

20. The rotor of claim 19 wherein the electrically conductive material is configured to prevent the flow of eddy currents within the electrically conductive material.

5 21. The rotor of claim 20 wherein the outer layer comprises multiple layers aluminum coated mylar.

22. The rotor of claim 21 wherein the aluminum coating includes segments whereby electric current does not flow in a direction along the axis of the rotor.

10 23. The rotor of claim 17 further comprising a banding concentrically arranged about the outer layer.

24. A machine comprising:

a rotor, said rotor comprising

15 a high temperature superconducting field winding,

a field winding support for securing the field winding, the support being electrically isolated from the field winding,

20 an AC flux shield concentrically arranged about the field winding,

and a thermal reserve concentrically arranged about the AC flux shield; and
a stator concentrically arranged about the rotor.

25 25. The machine of claim 24 further comprising a cryogenic refrigeration system thermally coupled to the rotor.

26. A method of limiting the rate of increase in the temperature of a superconducting winding, comprising:

- 15 -

concentrically arranging a thermal reserve about and in thermal contact with the superconducting winding.

27. The method of claim 26 wherein the thermal reserve comprises a thermally conducting material.

5 28. The method of claim 27 further comprising:
concentrically arranging a thermally
nonconductive material about the thermally conductive
material.

10 29. The method of claim 26 further comprising:
configuring the thermal reserve to suppress
electric eddy currents from flowing about the
superconducting winding.

Fig. 1




Fig. 2




Fig 3




Fig. 4




Fig.
5A.




Fig.
5B.





Fig. 6



INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/04298

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : H02K 19/02, 55/00, 55/02, 55/04
US CL : 310/162, 261

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols):

U.S. : 310/162, 261

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
NONEElectronic data base consulted during the international search (name of data base and, where practicable, search terms used)
NONE

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X --- Y --- A	US 4,152,609 A (COOPER et al.) 01 May 1979 (01-05-1979), col. 3, lines 21-23, col.4, lines 46-55, col. 5 lines 30-34, and col. 6, lines 16-20.	1, 2, 7, 9 ----- 8, 11-13, 26-27 ----- 4-6, 10, 14-16, 18, 21-23, 28-29
Y	US 5,777,420 A (GAMBLE et al.) 07 July 1998 (07-07-1998), col. 5, lines 45-47 and Fig. 8.	1-3, 17, 19-20, 24-25
Y	US 4,267,473 A (GAMBLE et al.) 12 MAY 1981 (12-05-1981), see entire document.	1-3, 8, 11-13, 17, 19-20, 24-27

☐ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

03 MAY 2000

Date of mailing of the international search report

20 JUN 2000

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

BURTON S. MULLINS

Telephone No. (703) 308-1371